

AV4 mil Silver 20

MECHANICAL PROPERTIES

Thickness	120 Micron
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

	4mm Single Pane
Visible Light Transmitted	18 %
Visible Light Reflected (Int)	58 %
Visible Light Reflected (Ext)	60 %
Ultra Violet Block	99 %
Total Solar Energy Reflected	56 %
Total Solar Energy Transmitted	11 %
Total Solar Energy Absorbed	33 %
Emissivity (Room Side)	0.74
Glare Reduction	83 %
Shading Coefficient	0.2
Solar Heat Gain Coeff. (G-Value)	0.2
U-Value Winter (IP)	0.99
U-Value Winter (SI)	5.1
Luminous Efficacy	0.70
Total Solar Energy Rejected	80 %

ACCREDITATIONS

Impact EN 12600 Class 2B2 ✓

REACH RoHS compliant: RESPECTED

AV4 mil Silver 20

Combines shard protection with high levels of energy savings that can enable a significant return on investment. It also combines the reinforced protection of security laminates with the superb heat rejection, UV block and sophisticated appearance of SolarZone films.

This product carries a full 10 years Manufacturer's warranty when professionally installed.

This film is available in 60" and 48" widths.

Please note: There may be restrictions concerning the suitability of this product to certain glazing types. If you would like general advice, please contact your supplier.
