


# Silver 35 Low-E

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	27 %	20 %
Visible Light Reflected (Int)	49 %	50 %
Visible Light Reflected (Ext)	44 %	46 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	41 %	38 %
Total Solar Energy Transmitted	19 %	17 %
Total Solar Energy Absorbed	40 %	45 %
Emissivity (Room Side)	0.45	0.45
Glare Reduction	70 %	69 %
Shading Coefficient	0.33	0.43
Solar Heat Gain Coeff. (G-Value)	0.28	0.37
U-Value Winter (IP)	0.83	0.42
U-Value Winter (SI)	4.71	2.38
Luminous Efficacy	0.80	0.58
Total Solar Energy Rejected	72 %	63 %

R06934E - Silver 35 Low-E Pressure Sensitive Adhesive



Ed-B DS No August 2011