

# OptiTune 22

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	21 %	19 %
Visible Light Reflected (Int)	15 %	15 %
Visible Light Reflected (Ext)	32 %	35 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	31 %	31 %
Total Solar Energy Transmitted	18 %	16 %
Total Solar Energy Absorbed	51 %	53 %
Emissivity (Room Side)	0.80	0.80
Glare Reduction	77 %	76 %
Shading Coefficient	0.38	0.51
Solar Heat Gain Coeff. (G-Value)	0.33	0.44
U-Value Winter (IP)	1.02	0.48
U-Value Winter (SI)	5.79	2.70
Luminous Efficacy	0.55	0.38
Total Solar Energy Rejected	67 %	56 %

R069R2W - OptiTune 22 Water Activated Adhesive

