


# Solar Bronze 35

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	33 %	31 %
Visible Light Reflected (Int)	29 %	30 %
Visible Light Reflected (Ext)	30 %	33 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	44 %	40 %
Total Solar Energy Transmitted	21 %	18 %
Total Solar Energy Absorbed	35 %	42 %
Emissivity (Room Side)	0.70	0.70
Glare Reduction	63 %	63 %
Shading Coefficient	0.35	0.44
Solar Heat Gain Coeff. (G-Value)	0.30	0.38
U-Value Winter (IP)	0.97	0.46
U-Value Winter (SI)	5.51	2.62
Luminous Efficacy	0.94	0.68
Total Solar Energy Rejected	70 %	62 %

R069B5W - Solar Bronze 35 Water Activated Adhesive

R069B5S - Solar Bronze 35 Pressure Sensitive Adhesive



ED - A DS No 1501 August 2011